

## OVERVIEW TECHNICAL DATA

# PressTherm® WD 20

<b>Product description</b>	Engineered composite material made of resin-bound glass fabric
<b>Standard colour</b>	yellow-brown
<b>Main applications</b>	Thermal insulation parts for heated presses
<b>Delivery program</b>	Sheets, panels and highly precise machined parts and finished components

## Physical characteristics

Properties	Test Standard	Unit	Typical value
Specific gravity	ISO 1183	g/cm <sup>3</sup>	1,9
Water absorption	ISO 62	%	0,1

## Thermal characteristics

Properties	Test Standard	Unit	Typical value
Operating temperature, continuous	-	°C	200
Operating temperature, short-term	-	°C	210
Coeff. of linear thermal expansion	DIN 51045	10 <sup>-6</sup> x K <sup>-1</sup>	20
Thermal conductivity	DIN 52612	W/mK	0,21

## Mechanical characteristics

Properties	Test Standard	Unit	Typical value
Compressive strength at 23 °C	ISO 604	N/mm <sup>2</sup>	500
Compressive strength at 200 °C	ISO 604	N/mm <sup>2</sup>	260
Flexural strength at 23 °C	ISO 178	N/mm <sup>2</sup>	500
Modul of elasticity at 23 °C	ISO 178	N/mm <sup>2</sup>	21000
Rate of Settling at 200 °C and 30 N/mm <sup>2</sup>	-	%	1,0
Split load	DIN 53463	N	3500

Issue: 11/2014

The standard values shown in this data sheet are measured by standard test methods. Depending on operation terms and dimensions the material properties can differ from these values.

Please contact our applications and sales engineers to clarify the suitability of the material for your application.